

Polyvinyl Chloride PVC Resin L700 from Sinopec QILU Petrochemical company

Specifications :

Price	Contact us
Model Number	L700
Place of Origin	China
Payment Terms	T/T,L/C,D/P
Supply Ability	1000
Delivery Detail	3days--7days

Detail Introduction :

Product introduction

The products adopt the patent technology of Shin-Etsu Chemical Co., Ltd of Japan and Western chemical company of the United States, and introduce complete sets of equipment. Taking Vinyl chloride monomer as raw materials and the suspension polymerization process, we can provide PVC resin with different performance and application. The production capacity is about 600000 tons per year.

Physical and chemical properties

PVC is a non-crystalline polymer with glass transition temperature between 105 ~ 75 ° according to molecular weight. Compared with other general plastics, PVC has the characteristics of flame retardancy and irritation, good chemical corrosion resistance, electrical insulation, chemical stability and thermoplasticity. It is insoluble in water, alcohol, gasoline and can dissolve or expand in ether and ketone.

The appearance of PVC resin is white amorphous powder, particle size 60~250µm, bulk density 0.40 ~ 0.60g/ml, 100 ml, The viscosity of 100ml cyclohexanone solution contains 0.5g PVC is 80~160 ml/g, the plasticizer absorption content of 100g resin at room temperature is 20~30g.

Technical Data

Item	Unit	L-700	L-800	L-1000	L-1300	L-800F	L-1000F
Average polymerization degree	-	650-750	750-850	970-1070	1250-1350	750-850	970-1070
Apparent density.	g/ml	0.54-0.62	0.53-0.61	0.50-0.58	0.45-0.52	0.53-0.61	0.50-0.58
Volatile content (Including Water)	%?	0.2	0.2	0.2	0.2	0.2	0.2
Absorbion of plasticizer	g, ?	14	16	20	27	17	20

Residual vinyl chloride monomer content	ug/g,?	3.0	3.0	3.0	2.0	3.0	2
Sieve residue 250um Sieve 63um Sieve	%?20 %, ?95	2.0 95	2.0 95	2.0 95	2.0 95	2.0 95	9
"Fish eye"	PCS/400cm2,?	16	16	10	10	16	1
Impurity Particals	PCS, ?	16	16	16	16	16	1
Whiteness(160??after 10 min)	%, ?	75	75	78	78	78	7
Application		Transparent sheet, board, floorboard material and hard film, joints, valves, electrical parts, automobile parts and containers.	Transparent film, Packaging, cardboard, cabinets and floors. Toy, bottles and containers	Soft film, sheets, artificial leather, pipes, profiles, cable protection tubes, packaging film, sole and a variety of soft products.	Thin film, thin sheet, artificial leather conductor, cable sheath and various soft profiles.	Extruded profiles, wire and cable materials, flexible and rigid materials, but calendered materials and flexible films and plates.	F fi o n p n v s o in n

Packaging and transportation

This product is packed with composite kraft paper and woven bags. It is strictly forbidden to use sharp tools such as iron hooks in the process of transportation and loading and unloading, so as not to damage the packaging bags. The net weight of each bag is 25kg. Clean and covered transportation tools should be used during transportation to prevent the rain. Goods should be stored in a dry and well ventilated warehouse.